

Acronal[®] V 212

Adhesive Raw Materials



We create chemistry

Chemicals nature

Aqueous dispersion of a carboxylic acrylic ester copolymer

Technical data

Solids content	approx. 69%
pH value	approx. 3.5 – 6
Viscosity	approx. 300 – 1100 mPa·s
Glass transition temperature of film	approx. – 40 °C

For detailed information see Specification data sheet.

Advantages

Acronal V 210 is used to manufacture pressure-sensitive adhesives for self-adhesive articles. It is distinguished by

its good adhesive properties, even at low temperatures. It also has low sensitivity to water and it adheres very well to rigid and plasticized PVC film, polyester film, and polyethylene and polypropylene film treated by corona discharge, with or without an adhesion promoter.

Applications

The pH should be in the weakly alkaline range when Acronal V 212 is mixed with other polymer dispersions. Please note that raising the pH causes the viscosity to increase. The mechanical stability of adhesives can be improved by adding a small amount of thickener. Wetting problems can often be overcome by adding around 0.5 % of a surfactant such as Lumiten[®] I-SC.

We would recommend adding preservatives to adhesives that contain Acronal V 212 to protect them from microbial attack. The suitability of such additives must be verified and monitored in trials.

Adhesives based on Acronal V 212 can be applied with the usual coating systems, e. g. doctor blade, wire-wound roll, air knife, reverse roll coating, reverse gravure coating, curtain coating and jet applicators.

Customers have to carry out their own trials when developing and processing pressure-sensitive adhesives based on Acronal V 212. The compatibility of Acronal V 212 with other ingredients of formulations and its ability to wet and adhere to different substrates, etc., are affected by a variety of factors which are too numerous for us to take into account in our own trials.

BASF SE
Regional Business Unit
Dispersions and Resins Europe
67056 Ludwigshafen, Germany

The data contained in this publication are based on our current knowledge and experience. They do not constitute the agreed contractual quality of the product and, in view of the many factors that may affect processing and application of our products, do not relieve processors from carrying out their own investigations and tests. The agreed contractual quality of the product at the time of transfer of risk is based solely on the data in the specification data sheet. Any descriptions, drawings, photographs, data, proportions, weights, etc. given in this publication may change without prior information. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

Edition: September 2008

TI/ED 1899 e

This data sheet will be rendered invalid if it is superseded by a later version.

® = registered trademark of BASF SE