

# Acronal<sup>®</sup> 3795

# **Adhesive Raw Material**

Product description	Acronal <sup>®</sup> 3795 forms a film with good immediate tack, high peel strength and good cohesion. It is used to manufacture pressure sensitive adhesives for selfadhesive articles.	
	Adhesives based on Acronal <sup>®</sup> 3795 also have good adhesive properties at low temperatures, are relatively insensitive to water, and adhere very well to films of plasticized and unplasticized PVC, polyester and electrically treated polyolefin films, even without an adhesion promoter.	
Chemical nature	Aqueous dispersion of a carboxyl-group- containing acrylate copolymer made with acrylonitrile.	

## Properties

**Physical form** 

Liquid

Technical data	Solid content	DIN EN ISO 3251	~ 55 %
(not supply specification)	pH value	DIN ISO 976	2.1 – 3.0
	Viscosity, dynamic, (23 °C, 250 1/s)	DIN EN ISO 3219	40 - 200 mPa s
	Glass transition temperature		-40 °C

## Application

When Acronal<sup>®</sup> 3795 is to be mixed with another dispersion, the pH can be raised to 6-8 which increases the mechanical stability.

Adhesives based on Acronal<sup>®</sup> 3795 can be applied to the carrier material with the usual coating systems, e. g. doctor blade, wire, air brush, reverse roll, reverse gravure, curtain and jet applicators.

In the event of poor wetting, it is often helpful to add about 0.5 % of a wetting agent such as Lumiten  $^{\otimes}$  I-SC.

We recommend adding a preservative to adhesives and coating materials that contain Acronal<sup>®</sup> 3795 to protect them from microbial attack, particularly if their pH lies in the neutral range. The suitability of such additives must be verified and monitored in trials.

Manufacturers must carry out thorough trials when they develop adhesives based on Acronal<sup>®</sup> 3795 . Their manufacture and use, their homogeneity, the compatibility of their components and their adhesion to, and interaction with different substrates etc. are affected by a host of factors that we cannot cover exhaustively in our own trials.

#### Safety

When handling this product, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

### Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

® = Registered trademark

™ = Trademark of the BASF Group, unless otherwise noted

BASF SE Dispersions Europe 67056 Ludwigshafen, Germany www.basf.com/dispersions