



Efka[®] FA 4606

Excellent dispersing agent for wood and industrial coatings

Performance Highlights

- Excellent for preventing hard settlement when dispersing matting agents, inorganic fillers and glass powders
- High pigments and filler loading
- Viscosity reduction with TiO₂ dispersion and other inorganic pigments
- Cost-effective

Characteristic Values

Appearance	Clear and yellowish liquid
Density at 20°C	0.97 g/cm ³
Active Ingredients	51%
Acid Value	54 mg KOH/g



Suitable for wood and industrial coatings

Efka® FA 4606

Excellent dispersing agent for inorganic pigments, fillers and matting agents for wood and industrial coatings

Efka® FA 4606 is a low molecular weight wetting and dispersing agent designed for excellent efficiency in dispersing and stabilizing fillers, matting agents and inorganic pigments in solvent-based systems.


Efka® FA 4606 is best suited for use in glass powder containing wood coatings formulations, which offers outstanding anti-settling properties. It is also recommended for use in other industrial coatings formulations.

Comparison of Efka® FA 4606 with competitors' products


The diagrams below illustrates the performance on storage stability and dispersing efficiency of Efka® FA 4606 versus the competition.

Anti-settling properties in 2K PU* (Based on soya short oil alkyd)

*Formulation containing glass powders



Dispersing efficiency in TiO₂ @ 60% TiO₂ at low dosage DOP 1%



Efka® FA 4606 enable formulators to achieve excellent anti-settling and dispersing properties with paints formulations

Contacts

Please contact our technical service department for more help on formulating with products from the Dispersing Agents product line.

Asia
BASF East Asia Regional HQ Ltd.
45/F., Jardine House
No.1 Connaught Place
Central
Hong Kong
formulation-additives-asia
@basf.com

Europe, Africa, West Asia
BASF SE
Formulation Additives
67056 Ludwigshafen
Germany
formulation-additives-europe
@basf.com

North America
BASF Corporation
11501 Steel Creek Road
Charlotte, NC 28273
USA
formulation-additives-nafta
@basf.com

South America
BASF S.A.
Rochaverá- Crystal Tower
Av. das Nações Unidas, 14.171
Morumbi - São Paulo-SP
Brazil
formulation-additives-south-america
@basf.com

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed. When handling these products, advice and information given in the safety data sheet must be complied with. Further, protective and workplace hygiene measures adequate for handling chemicals must be observed. (01/2018)

® = Registered trademark of the BASF Group