

Luphen[®] D 207 E

Adhesive Raw Materials



Chemical nature

Aqueous dispersion of a polyester-polyurethane elastomer

Technical data

Solids content	approx. 45 %
pH	approx. 7.0–9.0
Viscosity	approx. 30–100 mPas
Glass transition temperature	approx. –48 °C
Water absorption of film after 24 h	approx. 8 %
Tensile strength of film	approx. 40 N/mm ²
Elongation at break	approx. 1000 %

For detailed information see Specification Data-Sheet.

Application area

Luphen D 207 E is used in the manufacture of adhesives for laminating and heat-sealing.

BASF SE
Regional Business Unit
Dispersions and Resins Europe
67056 Ludwigshafen, Germany

The film that Luphen D 207 E yields can be activated by heat and in common with the PUR elastomer films, it has a limited hot-tack life.

Processing

In order to prevent coagulation, it is important to make sure that none of the components has a pH of less than 7 when thickeners are added or when Luphen D 207 E is mixed with other products. Luphen D 207 E can only be mixed with anionic dispersions or with dispersions that contain a protective colloid.

Container, pipes and other equipment that come into contact with Luphen D 207 E must be made of corrosion-resistant materials such as 18/8 stainless steel or plastics to prevent coagulation.

Specially developed water-emulsifiable, polyfunctional isocyanates such as Basonat[®] F 200 WD can be added to adhesives formulated with Luphen D 207 E to improve the heat resistance of the bond and its resistance to hydrolysis.

The potlife of the adhesive depends on the reactivity of the isocyanate used, and this has to be determined in trials. If Luphen D 207 E is employed in heat-sealing adhesives, an emulsifier such as Lumiten[®] I-SC should be added to the polymer dispersion at a rate of up to 1 % in order to promote the wetting of the substrate during coating. We recommend adding a preservative to adhesives based on Luphen D 207 E to protect them from microbial attack. The suitability of such additives must be verified and monitored in trials. Manufacturers must carefully carry out their own trials when developing adhesives based on Luphen D 207 E, as there is a host of factors in production and processing that we cannot cover exhaustively in our trials which can influence compatibility with other components of the adhesives, their wetting of and adhesion to different substrates etc. Particular attention is drawn to the fact that polyurethanes can be affected by hydrolysis and by exposure to heat, and comprehensive tests therefore need to be performed on adhesive formulations.

The data contained in this publication are based on our current knowledge and experience. They do not constitute the agreed contractual quality of the product and, in view of the many factors that may affect processing and application of our products, do not relieve processors from carrying out their own investigations and tests. The agreed contractual quality of the product at the time of transfer of risk is based solely on the data in the specification data sheet. Any descriptions, drawings, photographs, data, proportions, weights, etc. given in this publication may change without prior information. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

Edition: May 2016

TI/ED 1845 e

This data sheet will be rendered invalid if it is superseded by a later version.

® = registered trademark of BASF SE